



Optimization of pyrolysis conditions for char production from rice husks and its characterization as a precursor for production of activated carbon

E. Menya^{1,2} · P. W. Olupot¹ · H. Storz³ · M. Lubwama¹ · Y. Kiros⁴ · M. J. John⁵

Received: 12 December 2018 / Revised: 22 February 2019 / Accepted: 25 February 2019
© Springer-Verlag GmbH Germany, part of Springer Nature 2019

Abstract

Response surface methodology was employed to optimize pyrolysis conditions for production of char with maximum yield, fixed carbon content, and with minimum ash content from Uganda's New Rice for Africa (NERICA) 1 rice husk variety. The aim was to obtain rice husk char with more suitable properties as an activated carbon precursor. Mathematical models were developed to explain the relationships between the experimental responses and the pyrolysis parameters of temperature (400–600 °C), heating rate (10–25 °C min⁻¹), and heating period (60–120 min). The optimized rice husk char was further characterized for elemental and proximate compositions, thermal behavior, specific surface area, as well as surface functional groups. Results from the analysis of variance (ANOVA) revealed that the quadratic model best fits each of the responses. Pyrolysis temperature had the greatest influence on each of the responses, followed by heating period, and lastly heating rate. Optimum pyrolysis conditions were found to be temperature (406 °C), heating rate (10 °C min⁻¹), and heating period (60 min), resulting in char yield, fixed carbon, and ash contents of 35.26, 55.39, and 35.01% dry basis, respectively. Compared to raw rice husk, the resulting rice husk char was found more suited as activated carbon precursor, due to its enriched carbon content (60.35%) and specific surface area (123.9 m² g⁻¹). Thermogravimetric analysis of the rice husk char revealed that thermal activation temperatures higher than 400 °C may be required to considerably devolatilize the char, forming a more porous activated carbon.

Keywords NERICA 1 rice husk · Pyrolysis · Optimization · Char yield · Fixed carbon · Ash content

1 Introduction

Pyrolysis is one of the sustainable ways of utilizing biomass waste, as opposed to open dumping and/or burning, which

usually lead to environmental pollution. During this process, biomass is thermochemically decomposed in an inert environment, under temperatures of less than 700 °C [1]. Moisture and volatiles are driven off from the biomass, with the latter having good prospects for utilization as raw materials for synthesis gas production [2], as well as for bio-oil production [3]. On the other hand, the solid carbonaceous residue (char) left behind, can be subsequently utilized as a fuel [4], catalyst for thermochemical cracking of bio-oil and tars [5], soil conditioner [6], adsorbent [7], or as activated carbon precursor [8]. The activated carbon resulting from activation of char could be employed either, as an adsorbent, or as an active material in the preparation of electrodes for high-performance supercapacitors, as well as lithium-ion batteries [9]. Therefore, aside from sustainably disposing of biomass waste, pyrolysis paves way for obtaining sustainable alternative precursors for production of value-added, eco-friendly products [10]. However, careful selection of biomass, as well as control of pyrolysis conditions, is desired, if maximum product yields, and quality are to be obtained [11].

✉ E. Menya
emenya@cedat.mak.ac.ug

¹ Department of Mechanical Engineering, College of Engineering, Design, Art and Technology, Makerere University, P.O. Box 7062, Kampala, Uganda

² Department of Biosystems Engineering, Gulu University, P.O. Box 166, Gulu, Uganda

³ Thuenen Institute of Agricultural Technology, Bundesallee 47, 38116 Braunschweig, Germany

⁴ Department of Chemical Engineering, KTH Royal Institute of Technology, SE-100 44 Stockholm, Sweden

⁵ Polymer and Composite Unit, Council for Scientific and Industrial Research, Port Elizabeth 6000, South Africa